





















ООО «Скайхим групп»  
123182, Россия, г.Москва  
ул.Маршала Василевского  
д.17, п.2, оф.12  
тел. +7 495 373 25 03  
тел. +7 925 165 69 61  
[www.skychem.ru](http://www.skychem.ru)  
[info@skychem.ru](mailto:info@skychem.ru)

## SOLVENT-BASED PASTES FOR TINTOMETRIC SYSTEM



	CODE	DESCRIPTION	COLOR INDEX	PIGMENT %	DENSITY	LIGHT FASTNESS		WEATHER FASTNESS		ACID	ALKALI	OVERSPRAY	HEAT STABILITY
						FULL SHADE	WHITE REDUCTION	FULL SHADE	WHITE REDUCTION				
	S100-0000	S-COLOR WHITE	PW 6	61	1,837	8	8	5	5	5	5	5	200°C
	S303-0000	S-COLOR COLD YELLOW	PY 151	21	1,049	8	7/8	5	4	5	3	5	200°C
	S305-0000	S-COLOR SOLID COLD YELLOW	PY 184	45	1,560	7/8	7/8	4/5	4/5	4/5	5	5	200°C
	S306-0000	S-COLOR SOLID WARM YELLOW	PY 184	45	1,570	7/8	8	4/5	5	4/5	5	5	200°C
	S302-0000	S-COLOR GOLD YELLOW	PY 83	14	1,032	6/7	4/5	3	1	5	5	4/5	200°C
	S301-0000	S-COLOR WARM YELLOW	PY 139	21	1,072	8	7/8	5	4	5	5	5	200°C
	S300-0000	S-COLOR OCHRE YELLOW	PY 42	50	1,603	8	8	5	4/5	5	5	5	180°C
	S304-0000	S-COLOR OXIDE YELLOW	PY 42	46	1,508	8	8	5	4/5	5	5	5	180°C
	S201-0000	S-COLOR LIGHT ORANGE	PO 67	20	1,077	8	8	4	3/4	1	5	5	200°C
	S200-0000	S-COLOR ORANGE	PO 36	25	1,090	8	7/8	5	3/4	5	5	5	160°C
	S801-0000	S-COLOR DEEP RED	PR 48:4	18	1,055	7/8	6	4/5	3	1	1	3/4	160°C
	S802-0000	S-COLOR BRIGHT RED	PR 170	25	1,065	7	5	3/4	2	5	5	5	160°C
	S803-0000	S-COLOR OXIDE RED	PR 101	57	1,842	8	8	5	4/5	5	5	5	180°C
	S701-0000	S-COLOR AMARANTH	PV 19	10	1,008	7/8	7	5	4	5	5	5	200°C
	S800-0000	S-COLOR MAGENTA	PR 122	6	1,008	7/8	7	5	4	5	5	5	200°C
	S700-0000	S-COLOR VIOLET	PV 23	6	1,024	8	7/8	4/5	4	5	5	5	160°C
	S401-0000	S-COLOR BLUE GREEN SHADE	PB 15:4	15	1,053	8	8	5	4/5	5	5	4/5	200°C
	S400-0000	S-COLOR BLUE RED SHADE	PB 15:2	13	1,046	8	8	5	4/5	5	5	4	200°C
	S900-0000	S-COLOR GREEN	PG 7	21	1,146	7/8	7	5	4/5	5	5	5	200°C
	S600-0000	S-COLOR SMOKE BLACK	PB 7	22	1,107	8	8	5	5	5	5	5	200°C
	S601-0000	S-COLOR DEEP BLACK	PB 7	9	1,031	8	8	5	5	5	5	5	200°C